

Westlake Plastics Radel® R 5500 Polyphenylsulfone

Category : Polymer , Thermoplastic , Polyphenylsulfone (PPSU)

Material Notes:

Stock shapes extruded from Radel R resins offer a superior combination of high performance properties that include excellent thermal stability, outstanding toughness, and good environmental stress cracking resistance. These properties make Radel R stock shapes attractive for a variety of demanding applications. The standard color of Radel R is off white, but a transparent grade is available. Radel® is a trade name of Solvay Advanced Polymers. Information provided by Westlake Plastics.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Westlake-Plastics-Radel-R-5500-Polyphenylsulfone.php

Physical Properties	Metric	English	Comments
Density	1.29 g/cc	0.0466 lb/in ³	ASTM D792
Water Absorption	0.37 %	0.37 %	ASTM D570; 24 hrs.

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	69.6 MPa	10100 psi	ASTM D638
Elongation at Break	60 - 120 %	60 - 120 %	ASTM D638
Elongation at Yield	7.2 %	7.2 %	ASTM D638
Tensile Modulus	2.34 GPa	340 ksi	ASTM D638
Flexural Yield Strength	91.0 MPa	13200 psi	ASTM D790
Flexural Modulus	2.41 GPa	350 ksi	ASTM D790
Compressive Yield Strength	98.94 MPa	14350 psi	ASTM D695
Compressive Modulus	1.73 GPa	251 ksi	ASTM D695
Izod Impact, Notched	6.94 J/cm	13.0 ft-lb/in	ASTM D256
Izod Impact, Unnotched	NB	NB	ASTM D256
Tensile Impact Strength	399 kJ/m ²	190 ft-lb/in ²	ASTM D1822

Thermal Properties	Metric	English	Comments
CTE, linear	55.8 µm/m-°C	31.0 µin/in-°F	ASTM D696
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Thermal Conductivity	0.349 W/m-K	2.42 BTU-in/hr-ft ² -°F	ASTM C177
Deflection Temperature at 0.46 MPa (66 psi)	214 °C	417 °F	ASTM D648

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	207 °C	405 °F	ASTM D648
Flammability, UL94	V-0 @Thickness 0.787 mm	V-0 @Thickness 0.0310 in	
Oxygen Index	38 %	38 %	ASTM D2863

Optical Properties	Metric	English	Comments
Haze	15 %	15 %	ASTM D1746
Transmission, Visible	50 %	50 %	ASTM D1746

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 1.00e+17 ohm-cm	>= 1.00e+17 ohm-cm	ASTM D257
Dielectric Constant	3.45 @Frequency 1000 Hz	3.45 @Frequency 1000 Hz	ASTM D150
Dielectric Strength	14.2 kV/mm	360 kV/in	ASTM D149
Dissipation Factor	0.00090 @Frequency 1000 Hz	0.00090 @Frequency 1000 Hz	ASTM D150

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China