

Wieland 3013 Wilaform Silver

Category : Metal , Nonferrous Metal , Precious Metal , Silver Alloy

Material Notes:

Universally applicable silver alloy.Applications: casting, chains, coin/shape, laminar decoration, pipes, tubingDental

Order this product through the following link:

http://www.lookpolymers.com/polymer_Wieland-3013-Wilaform-Silver.php

Physical Properties	Metric	English	Comments
Density	10.4 g/cc	0.376 lb/in ³	

Mechanical Properties	Metric	English	Comments
Hardness, Vickers	70	70	HV5; glowd
Tensile Strength, Ultimate	300 MPa	43500 psi	
Elongation at Break	30 %	30 %	

Thermal Properties	Metric	English	Comments
Melting Point	820 - 910 °C	1510 - 1670 °F	
Solidus	820 °C	1510 °F	
Liquidus	910 °C	1670 °F	

Component Elements Properties	Metric	English	Comments
Copper, Cu	6.5 %	6.5 %	
Silver, Ag	93.5 %	93.5 %	

Processing Properties	Metric	English	Comments
Processing Temperature	600.0 °C	1112 °F	Cuvette Temp
Casting Temperature	1010 - 1100 °C	1850 - 2010 °F	

Descriptive Properties	Value	Comments
Color	white	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China