

Wieland Auropal M-1 Solder

Category : Metal , Nonferrous Metal , Precious Metal , Gold Alloy , Solder/Braze Alloy

Material Notes:

Solder supplied as strip (0.18 oz. roll), triangular (7.09 in. rod)Information provided by WielandDental

Order this product through the following link:

http://www.lookpolymers.com/polymer_Wieland-Auropal-M-1-Solder.php

Component Elements Properties	Metric	English	Comments
Copper, Cu	7.0 %	7.0 %	
Gold, Au	62 %	62 %	
Indium, In	5.0 %	5.0 %	
Palladium, Pd	3.0 %	3.0 %	
Silver, Ag	17 %	17 %	
Zinc, Zn	6.0 %	6.0 %	

Processing Properties	Metric	English	Comments
Processing Temperature	800.0 °C	1472 °F	Flow Temp
Melt Temperature	710 - 770.0 °C	1310 - 1418 °F	

Descriptive Properties	Value	Comments
Color	yellow	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China