

## Wieland Bio Porta 1020 Solder

Category : Metal , Nonferrous Metal , Precious Metal , Gold Alloy , Silver Alloy , Solder/Braze Alloy

**Material Notes:**

Solder supplied as strip (0.18 oz. roll)Information provided by WielandDental

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Wieland-Bio-Porta-1020-Solder.php](http://www.lookpolymers.com/polymer_Wieland-Bio-Porta-1020-Solder.php)

| Component Elements Properties | Metric | English | Comments |
|-------------------------------|--------|---------|----------|
| Gold, Au                      | 73.5 % | 73.5 %  |          |
| Silver, Ag                    | 25 %   | 25 %    |          |
| Zinc, Zn                      | 1.5 %  | 1.5 %   |          |

| Processing Properties  | Metric        | English        | Comments  |
|------------------------|---------------|----------------|-----------|
| Processing Temperature | 1020 °C       | 1870 °F        | Flow Temp |
| Melt Temperature       | 960 - 1010 °C | 1760 - 1850 °F |           |

| Descriptive Properties | Value  | Comments |
|------------------------|--------|----------|
| Color                  | yellow |          |

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China