

## Wieland Porta Optimum 900 Solder

Category : Metal , Nonferrous Metal , Precious Metal , Gold Alloy , Solder/Braze Alloy

**Material Notes:**

Solder supplied as strip (0.18 oz. roll)Information provided by WielandDental

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Wieland-Porta-Optimum-900-Solder.php](http://www.lookpolymers.com/polymer_Wieland-Porta-Optimum-900-Solder.php)

Component Elements Properties	Metric	English	Comments
Gold, Au	88.7 %	88.7 %	
Iridium, Ir	0.10 %	0.10 %	
Platinum, Pt	2.0 %	2.0 %	
Silver, Ag	3.0 %	3.0 %	
Zinc, Zn	6.2 %	6.2 %	

Processing Properties	Metric	English	Comments
Processing Temperature	900.0 °C	1652 °F	Flow Temp
Melt Temperature	830.0 - 890.0 °C	1526 - 1634 °F	

Descriptive Properties	Value	Comments
Color	yellow	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China