

Zell-Metall Engineering Plastics Zellamid 1100 MO

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , MoS2 Filled

Material Notes:

Improved sliding and self lubricating properties are achieved by the addition of molybdenum disulphide. UV-radiation resistance is enhanced. Color: black Applications: For conveyor screws

Order this product through the following link:

http://www.lookpolymers.com/polymer_Zell-Metall-Engineering-Plastics-Zellamid-1100-MO.php

Physical Properties	Metric	English	Comments
Density	1.15 g/cc	0.0415 lb/in ³	
Moisture Absorption at Equilibrium	2.5 - 3.0 %	2.5 - 3.0 %	Saturation at 50% RH
Water Absorption at Saturation	6.0 - 7.0 %	6.0 - 7.0 %	23°C

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	83 - 85	83 - 85	DIN 53505
Ball Indentation Hardness	165 MPa	23900 psi	DIN 53456
Tensile Strength at Break	90.0 - 92.0 MPa	13100 - 13300 psi	DIN 53455
Elongation at Break	10 - 30 %	10 - 30 %	DIN 53455
Tensile Modulus	4.10 GPa	595 ksi	DIN 53457
	0.900 GPa	131 ksi	DIN 53457
	@Temperature 100 °C	@Temperature 212 °F	
Charpy Impact Unnotched	NB	NB	DIN 53453
Charpy Impact, Notched	2.20 - 2.80 J/cm ²	10.5 - 13.3 ft-lb/in ²	DIN 53453
Coefficient of Friction	0.050 - 0.10	0.050 - 0.10	to steel, added lubrication
	0.30 - 0.35	0.30 - 0.35	to steel, no lubrication; ISO/DTR 7147
Abrasion	91	91	mm ³ ; DIN 53516

Thermal Properties	Metric	English	Comments
CTE, linear	80.0 μm/m-°C	44.4 μin/in-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Specific Heat Capacity	1.67 J/g-°C	0.399 BTU/lb-°F	
Thermal Conductivity	0.280 W/m-K	1.94 BTU-in/hr-ft ² -°F	DIN 52612

Thermal Properties	Metric	English	Comments
Melting Point	220 °C	428 °F	
Maximum Service Temperature, Air	100 - 120 °C	212 - 248 °F	long time operation
	120 - 140 °C	248 - 284 °F	medium time operation
	160 °C	320 °F	a few hours operation
Minimum Service Temperature, Air	-40.0 °C	-40.0 °F	
Flammability, UL94	HB	HB	

Descriptive Properties	Value	Comments
Time yield limit	up to 5	s1/1000; DIN.53444

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China