

Zeon Chemicals HyTemp® 4052EP AR Polyacrylate Elastomer

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

Material Notes:

HyTemp 4052EP contains acrylic esters with a small percentage of a chlorine/carboxy cure site monomer. Vulcanizates have excellent oil, heat, and compression set resistance with good low temperature. Easy processing version of HyTemp 4052.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Zeon-Chemicals-HyTemp-4052EP-AR-Polyacrylate-Elastomer.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.10 g/cc	1.10 g/cc	
Mooney Viscosity	20 - 35 @Temperature 100 °C	20 - 35 @Temperature 212 °F	(1+4); Zeon Test #404
Ash	<= 0.50 %	<= 0.50 %	Zeon Test #873

Thermal Properties	Metric	English	Comments
Minimum Service Temperature, Air	-32.0 °C	-25.6 °F	Gehman T100
Glass Transition Temp, Tg	-33.1 - -25.2 °C	-27.6 - -13.4 °F	

Descriptive Properties	Value	Comments
% Volume Swell	17	
Curesite	Dual	
Gel-Mek (%), max	15	
Heat Loss (%) Max	0.7	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China