

Zeon Chemicals HyTemp® AR12 AR Super ACM Polyacrylate Elastomer

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Curesite is optimized for improved long-term heat and compression set resistance over traditional acrylates with good low-temperature properties.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Zeon-Chemicals-HyTemp-AR12-AR-Super-ACM-Polyacrylate-Elastomer.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.10 g/cc	1.10 g/cc	
Mooney Viscosity	30 - 36 @Temperature 100 °C	30 - 36 @Temperature 212 °F	(1+4)

Thermal Properties	Metric	English	Comments
Minimum Service Temperature, Air	-30.0 °C	-22.0 °F	Gehman T100

Descriptive Properties	Value	Comments
% Volume Swell	30	
Curesite	Proprietary	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China