

## Zeon Chemicals HyTemp® AR14 AR Super ACM Polyacrylate Elastomer

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

**Material Notes:**

Improved low-temperature version of AR12.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Zeon-Chemicals-HyTemp-AR14-AR-Super-ACM-Polyacrylate-Elastomer.php](http://www.lookpolymers.com/polymer_Zeon-Chemicals-HyTemp-AR14-AR-Super-ACM-Polyacrylate-Elastomer.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.10 g/cc	1.10 g/cc	
Mooney Viscosity	28 - 38 @Temperature 100 °C	28 - 38 @Temperature 212 °F	(1+4)

Thermal Properties	Metric	English	Comments
Minimum Service Temperature, Air	-40.0 °C	-40.0 °F	Gehman T100

Descriptive Properties	Value	Comments
% Volume Swell	27	
Curesite	Proprietary	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China