

Zeon Chemicals HyTemp® AR212HR Polyacrylate Curative

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

Material Notes:

HyTemp AR212HR acrylic elastomer contains one or more acrylic esters with a small percentage of a proprietary cure site. Vulcanizates have excellent oil, heat and compression resistance. Acrylic elastomer contains one or more acrylic esters with a small percentage of a proprietary cure site. Vulcanizates have excellent oil, heat and compression resistance.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Zeon-Chemicals-HyTemp-AR212HR-Polyacrylate-Curative.php

Physical Properties	Metric	English	Comments
Mooney Viscosity	30 - 45	30 - 45	Zeon Test #404
Ash	<= 0.30 %	<= 0.30 %	Zeon Test #873

Thermal Properties	Metric	English	Comments
Glass Transition Temp, Tg	-24.5 °C	-12.1 °F	Zeon Test #1273

Descriptive Properties	Value	Comments
Heat Loss (%) Max	0.7	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China