

## Zeon Chemicals Nipol® 33-5HM Nitrile Elastomer

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

### Material Notes:

Low mold fouling, high-modulus, 55 Mooney nitrile rubber, recommended for high temperature injection molding. Low mold fouling, high-modulus, 55 Mooney nitrile rubber. Recommended for high temperature injection molding.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Zeon-Chemicals-Nipol-33-5HM-Nitrile-Elastomer.php](http://www.lookpolymers.com/polymer_Zeon-Chemicals-Nipol-33-5HM-Nitrile-Elastomer.php)

Physical Properties	Metric	English	Comments
Specific Gravity	0.980 g/cc	0.980 g/cc	
Mooney Viscosity	47 - 57 @Temperature 100 °C	47 - 57 @Temperature 212 °F	(1+4)
Ash	<= 0.75 %	<= 0.75 %	T-4210

Descriptive Properties	Value	Comments
AO Type	NS	
Bound ACN (% acrylonitrile)	32-34	
Heat Loss (%) Max	0.5	
Hot/Cold	C	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China