

## **Zeon Chemicals Nipol® 9025 Polyblack Masterbatch**

Category: Polymer, Thermoset, Rubber or Thermoset Elastomer (TSE)

## **Material Notes:**

Recommended for use in extruded goods requiring medium-high solvent and oil resistance. Based on Nipol 35-5 with 75 phr of N660 black. Recommended for use in extruded goods requiring medium-high solvent and oil resistance.

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_Zeon-Chemicals-Nipol-9025-Polyblack-Masterbatch.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.25 g/cc	1.25 g/cc	
Mooney Viscosity	85 - 115	85 - 115	(CML 1+4); T-4500
Carbon Black Loading	40.6 - 44.4 %	40.6 - 44.4 %	
Ash	4.0 - 7.0 %	4.0 - 7.0 %	

Descriptive Properties	Value	Comments
AO Type	NS	
Bound ACN (%, acrylonitrile)	35	
Gel-Mek (%)	75-85	
Heat Loss (%) Max	0.75	
Hot/Cold	С	
Nipol Base Polymer	35-5	

## **Contact Songhan Plastic Technology Co.,Ltd.**

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China