

## Zhejiang Juner JEPP2056 PP For Automotive Parts

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Molded

**Material Notes:**

Applications: Bumpers Information provided by Zhejiang Juner New Materials Co, Ltd.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Zhejiang-Juner-JEPP2056-PP-For-Automotive-Parts.php](http://www.lookpolymers.com/polymer_Zhejiang-Juner-JEPP2056-PP-For-Automotive-Parts.php)

Physical Properties	Metric	English	Comments
Density	0.980 g/cc	0.0354 lb/in <sup>3</sup>	GB/1033
Linear Mold Shrinkage	0.011 - 0.013 cm/cm	0.011 - 0.013 in/in	GB/15585
Melt Flow	1.0 - 1.3 g/10 min	1.0 - 1.3 g/10 min	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	20.0 MPa	2900 psi	GB/1040
Flexural Strength	20.0 MPa	2900 psi	GB/9341
Charpy Impact Unnotched	NB	NB	ISO179-1:2000
Charpy Impact, Notched	5.00 J/cm <sup>2</sup>	23.8 ft-lb/in <sup>2</sup>	ISO179-1:2000

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	95.0 °C	203 °F	GB1634

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+18 ohm-cm	1.00e+18 ohm-cm	D257

Processing Properties	Metric	English	Comments
Processing Temperature	170 - 230 °C	338 - 446 °F	
Mold Temperature	40.0 - 80.0 °C	104 - 176 °F	
Injection Pressure	30.0 - 90.0 MPa	4350 - 13100 psi	

Descriptive Properties	Value	Comments
Speed of Shoot, %	35-85	

**Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215, Fengxian District, Shanghai City, China**