

## Zhejiang Juner JEPPBC001 Weatherability PP Series

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Molded

### Material Notes:

Applications: Weatherability Products Information provided by Zhejiang Juner New Materials Co, Ltd.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Zhejiang-Junere-JEPPBC001-Weatherability-PP-Series.php](http://www.lookpolymers.com/polymer_Zhejiang-Junere-JEPPBC001-Weatherability-PP-Series.php)

Physical Properties	Metric	English	Comments
Density	1.02 g/cc	0.0368 lb/in <sup>3</sup>	GB/1033
Linear Mold Shrinkage	0.012 cm/cm	0.012 in/in	GB/15585
Melt Flow	8.0 g/10 min	8.0 g/10 min	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	25.0 MPa	3630 psi	GB/1040
Flexural Strength	40.0 MPa	5800 psi	GB/9341
Charpy Impact Unnotched	NB	NB	ISO179-1:2000
Charpy Impact, Notched	1.00 J/cm <sup>2</sup>	4.76 ft-lb/in <sup>2</sup>	ISO179-1:2000

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	125 °C	257 °F	GB1634

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+18 ohm-cm	1.00e+18 ohm-cm	D257

Processing Properties	Metric	English	Comments
Processing Temperature	160 - 250 °C	320 - 482 °F	
Mold Temperature	40.0 - 80.0 °C	104 - 176 °F	
Drying Temperature	85.0 °C @Time 10800 sec	185 °F @Time 3.00 hour	Horizontal Oven
	90.0 °C @Time 7200 sec	194 °F @Time 2.00 hour	Chute Hot-Wind
Injection Pressure	40.0 - 90.0 MPa	5800 - 13100 psi	

Descriptive Properties	Value	Comments
Speed of Shoot, %	35-85	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China