

Zhejiang Juner PA66-301-HG30 Flame-Retardant & Glass Reinforced, Environmental PA66

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, Glass Fiber Filled, Flame Retardant

Material Notes:

Applications: Connector AS Pedestal Information provided by Zhejiang Juner New Materials Co, Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Zhejiang-Juner-PA66-301-HG30-Flame-Retardant-Glass-Reinforced-Environmental-PA66.php

Physical Properties	Metric	English	Comments
Density	1.56 g/cc	0.0564 lb/in ³	GB/1033
Water Absorption	0.60 %	0.60 %	23°C•24h
Linear Mold Shrinkage	0.010 cm/cm	0.010 in/in	GB/15585

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	137 MPa	19900 psi	GB/1040
Flexural Strength	209 MPa	30300 psi	GB/9341
Charpy Impact Unnotched	3.50 J/cm ²	16.7 ft-lb/in ²	ISO179-1:2000
Charpy Impact, Notched	0.820 J/cm ²	3.90 ft-lb/in ²	ISO179-1:2000

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	230 °C	446 °F	GB1634
Flammability, UL94	V-0	V-0	GB/T2408
Flammability Test	30	30	Flame Remainder (%); GB/9345

Processing Properties	Metric	English	Comments
Processing Temperature	255 - 285 °C	491 - 545 °F	
Mold Temperature	60.0 - 120 °C	140 - 248 °F	
Drying Temperature	110 °C	230 °F	Vacuum Pressure, -0.08 MPa
	@Time 10800 sec	@Time 3.00 hour	
	120 °C	248 °F	Chute Hot-Wind
	@Time 18000 sec	@Time 5.00 hour	
	120 °C	248 °F	

Processing Properties	Metric @ Time 21600 sec	English @ Time 6.00 hour	Horizontal Oven Comments
Injection Pressure	50.0 - 120 MPa	7250 - 17400 psi	

Descriptive Properties	Value	Comments
Speed of Shoot, %	35-90	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China