

## Zig Sheng Industrial ZISAMIDE® TP4208 Nylon 6

Category : Polymer , Thermoplastic , Nylon , Nylon 6

**Material Notes:**

ZISAMIDE® TP4208 is a Polyamide 6. Application: compounding injection Information provided by ZIG SHEN Industrial Co., LTD.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Zig-Sheng-Industrial-ZISAMIDE-TP4208-Nylon-6.php](http://www.lookpolymers.com/polymer_Zig-Sheng-Industrial-ZISAMIDE-TP4208-Nylon-6.php)

| Physical Properties    | Metric             | English            | Comments |
|------------------------|--------------------|--------------------|----------|
| Melt Index of Compound | 180 - 230 g/10 min | 180 - 230 g/10 min |          |

| Thermal Properties | Metric       | English      | Comments |
|--------------------|--------------|--------------|----------|
| Melting Point      | 220 - 225 °C | 428 - 437 °F |          |

| Processing Properties | Metric    | English   | Comments |
|-----------------------|-----------|-----------|----------|
| Moisture Content      | <= 0.10 % | <= 0.10 % |          |

| Descriptive Properties   | Value  | Comments |
|--------------------------|--------|----------|
| Amino End Group (meq/kg) | 44 ± 3 |          |
| Extractable (%max)       | < 0.6  |          |

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China