

Zircar Refractory Composites RS-C ALUMINA-SILICA MOLDABLE

Category : Ceramic , Oxide , Aluminum Oxide , Silicon Oxide

Material Notes:

ZIRCAR Alumina-Silica Insulating Blanket Type RS-C Moldable is composed of long, high strength ceramic fibers, with an inorganic alumina binder/rigidizing agent. It is a wet blanket that is shipped rolled up and sealed in a plastic bag to preserve its moldability. Information provided by ZIRCAR Refractory Composites, Inc. (ZRCI)

Order this product through the following link:

http://www.lookpolymers.com/polymer_Zircar-Refractory-Composites-RS-C-ALUMINA-SILICA-MOLDABLE.php

Physical Properties	Metric	English	Comments
Density	0.460 g/cc	0.0166 lb/in ³	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	0.480 MPa	69.6 psi	
Compressive Yield Strength	0.200 MPa	29.0 psi	at 10% Compression

Thermal Properties	Metric	English	Comments
Thermal Conductivity	0.0600 W/m-K	0.416 BTU-in/hr-ft ² -°F	ASTM C177
	@Temperature 200 °C	@Temperature 392 °F	
	0.130 W/m-K	0.902 BTU-in/hr-ft ² -°F	ASTM C177
	@Temperature 500 °C	@Temperature 932 °F	
	0.200 W/m-K	1.39 BTU-in/hr-ft ² -°F	ASTM C177
	@Temperature 800 °C	@Temperature 1470 °F	
Maximum Service Temperature, Air	1260 °C	2300 °F	
Shrinkage	0.000 %	0.000 %	Drying
	@Temperature 75.0 °C	@Temperature 167 °F	
	2.00 %	2.00 %	
	@Temperature 800 °C, Time 86400 sec	@Temperature 1470 °F, Time 24.0 hour	

Component Elements Properties	Metric	English	Comments
Al2O3	66 %	66 %	
SiO2	34 %	34 %	

Descriptive Properties	Value	Comments
Color	White	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China