

## BIW ASTM Class 2D0 Silicone Foam

Category : Polymer , Thermoset , Silicone , Silicone Foam

**Material Notes:**

Products are a closed cell foam and there fore good for use in damp or liquid applications. A variety of physical properties and foam qualities are available by adjusting the processing parameters. Information provided by BIW Isolierstoffe GmbH.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_BIW-ASTM-Class-2D0-Silicone-Foam.php](http://www.lookpolymers.com/polymer_BIW-ASTM-Class-2D0-Silicone-Foam.php)

Physical Properties	Metric	English	Comments
Density	<= 0.280 g/cc	<= 0.0101 lb/in <sup>3</sup>	DIN 53479 A

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	<= 5	<= 5	DIN 53505
Compressive Yield Strength	<= 0.0150 MPa	<= 2.18 psi	25% Compression
Compression Set	<= 80 % @Temperature 100 °C, Time 79200 sec	<= 80 % @Temperature 212 °F, Time 22.0 hour	50% Compression

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	180 °C	356 °F	Standard Quality, All Colors
	280 °C	536 °F	Highly Temperature Resistant Quality, Opaque, Grey, Blue
Minimum Service Temperature, Air	-60.0 °C	-76.0 °F	Standard Quality, All Colors

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China