

## Denka REOMER G G5072 Thermoplastic Elastomer, For Extrusion

Category : Polymer , Thermoplastic , Elastomer , TPE

### Material Notes:

Essentially a thermoplastic elastomer with the characteristics of PVC resin and rubber, with excellent rubber-like elasticity. Offers excellent rubbery characteristics, such as permanent compressive distortion, rebound elasticity, etc. compared to soft PVC, and excellent bending strength and ozone resistance compared to rubber. Applications: Automotive components, door moldings, weather-strips, glass run channels, side bumpers, gaskets, mud flaps, head rests, arm rests, steering wheel trim, shift bar boots, pedal pads. Construction material, manufacturing article, home electric, appliance components. Gaskets, airtight materials, container packing, packing for vacuum cleaners, hoses, tubes. For electric wire, appliance cords, cable tire.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Denka-REOMER-G-G5072-Thermoplastic-Elastomer-For-Extrusion.php](http://www.lookpolymers.com/polymer_Denka-REOMER-G-G5072-Thermoplastic-Elastomer-For-Extrusion.php)

Physical Properties	Metric	English	Comments
Density	1.29 g/cc	0.0466 lb/in <sup>3</sup>	JIS-Z-8807
Evaporation Loss	5.0 %	5.0 %	JIS-A-5756

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	72	72	JIS-K-6301
Tensile Strength at Break	16.78 MPa	2433 psi	JIS-K-6723
Elongation at Break	360 %	360 %	JIS-K-6723
100% Modulus	0.0063765 GPa	0.92485 ksi	JIS-K-6723
Resilience	25	25	JIS-K-6301
Compression Set	55 %	55 %	JIS-K-6301

Thermal Properties	Metric	English	Comments
Minimum Service Temperature, Air	-43.0 °C	-45.4 °F	JIS-K-6723

Descriptive Properties	Value	Comments
Bending Strength, Times, JIS-K-6301	over 100k	
Heating: Retention Rate of Elongation, %	93	100°C x 120 hrs
Heating: Retention Rate of Tensile Strength, %	103	100°C x 120 hrs
Oil Resistance: Retention of Tensile Strength, %	92	JIS-K-6723
Oil Resistance: Retention Rate of Elongation, %	80	JIS-K-6723

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**