

DuPont Performance Polymers Crastin® SK602 BK851 Polybutylene Terephthalate (PBT) (Unverified Data**)

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), 20% Glass Fiber Filled

Material Notes:

15% Glass Reinforced Polybutylene Terephthalate Crastin SK602 BK851 is a 15% glass fiber reinforced lubricated black polybutylene terephthalate resin for injection molding. Information provided by DuPont Performance Polymers

Order this product through the following link:

http://www.lookpolymers.com/polymer_DuPont-Performance-Polymers-Crastin-SK602-BK851-Polybutylene-Terephthalate-PBT-nbspUnverified-Data.php

Physical Properties	Metric	English	Comments
Density	1.41 g/cc	0.0509 lb/in ³	ISO 1183

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	102 MPa	14800 psi	ISO 527-1/-2
Elongation at Break	3.4 %	3.4 %	ISO 527-1/-2
Tensile Modulus	5.70 GPa	827 ksi	ISO 527-1/-2
Izod Impact, Notched (ISO)	5.00 kJ/m ²	2.38 ft-lb/in ²	ISO 180/1A
Charpy Impact Unnotched	4.00 J/cm ²	19.0 ft-lb/in ²	ISO 179/1eU
Charpy Impact, Notched	0.600 J/cm ²	2.86 ft-lb/in ²	ISO 179/1eA

Thermal Properties	Metric	English	Comments
Melting Point	225 °C	437 °F	10°C/min; ISO 11357-1/-3
Deflection Temperature at 1.8 MPa (264 psi)	200 °C	392 °F	ISO 75-1/-2
Flammability, UL94	HB @Thickness 1.50 mm	HB @Thickness 0.0591 in	IEC 60695-11-10

Descriptive Properties	Value	Comments
Part Marking Code	>PBT-GF15<	ISO 11469
Processing	Injection Moulding	
Regional Availability	Asia Pacific	
	Europe	
	Global	

Descriptive Properties	Value	Comments
	Near East/Africa	
	North America	
	South and Central America	
Resin Identification	PBT-GF15	
UL recognition	UL	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China