

Elisto THERMOSTAR® LC 6000 Insulation Material

Category : Other Engineering Material

Material Notes:

Pattern material. Insulation materials for mechanical engineering. Information provided by elisto

Order this product through the following link:

http://www.lookpolymers.com/polymer_Elisto-THERMOSTAR-LC-6000-Insulation-Material.php

Mechanical Properties	Metric	English	Comments
Flexural Strength	150 MPa	21800 psi	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Compressive Strength	100 MPa	14500 psi	
	@Temperature 200 °C	@Temperature 392 °F	
	340 MPa	49300 psi	
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Thermal Conductivity	0.140 W/m-K	0.972 BTU-in/hr-ft ² -°F	
Maximum Service Temperature, Air	200 °C	392 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China