

Huntsman HT 3261 Special Hardener

Category : Polymer , Thermoset , Epoxy , Epoxy Cure Resin

Material Notes:

Mix Ratio with 100 phr GT 70130 is 6. Comments/Applications: Solid resinous amino-containing hardener. *Mix ratio with Araldite GT 7013. For low temperature cure, high gloss. Decorative and protective powder coatings. Data provided by Ciba Specialty Chemicals. Ciba Specialty Chemicals has been acquired by Huntsman.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Huntsman-HT-3261-Special-Hardener.php

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	90.0 - 100 Â°C	194 - 212 Â°F	Softening Range

Processing Properties	Metric	English	Comments
Processing Temperature	120 Â°C	248 Â°F	Cure Schedule: 15 min @ 120Â°C

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China