

## Lucent Polymers PC-1418 Polycarbonate, Injection Grade

Category : Polymer , Thermoplastic , Polycarbonate (PC)

**Material Notes:**

High FlowAdd "R" for Added ReleaseAdd "U" for UVÂ StabilizedInformation provided by Lucent Polymers, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Lucent-Polymers-PC-1418-Polycarbonate-Injection-Grade.php](http://www.lookpolymers.com/polymer_Lucent-Polymers-PC-1418-Polycarbonate-Injection-Grade.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.21 g/cc	1.21 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.0060 cm/cm @Thickness 3.17 mm	0.0060 in/in @Thickness 0.125 in	1/8" Section
Melt Flow	18 g/10 min	18 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	62.07 MPa	9003 psi	ASTM D638
Elongation at Break	>= 132 %	>= 132 %	ASTM D638
Flexural Strength	98.62 MPa	14300 psi	ASTM D790
Flexural Modulus	2.276 GPa	330.1 ksi	ASTM D790
Izod Impact, Notched	6.41 J/cm @Thickness 3.17 mm, Temperature 22.8 Â°C	12.0 ft-lb/in @Thickness 0.125 in, Temperature 73.0 Â°F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	132.22 Â°C	270.00 Â°F	ASTM D648

### Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China