

PolyOne OnFlex™ S EF 60A-3S1967 Thermoplastic Elastomer (TPE)

Category : Polymer , Thermoplastic , Elastomer, TPE

Material Notes:

OnFlex™-S EF thermoplastic elastomer compounds are based on hydrogenated styrenic block copolymers. This range of compounds are formulated to deliver good mechanical properties together with excellent processability, in addition to typical OnFlex™-S properties such as a wide hardness range, low compression set, good colourability and a wide temperature operating range. OnFlex™-S EF compounds are semi-filled, making them opaque and with a medium density. Properties are measured using injection molded plaques. Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-OnFlex-S-EF-60A-3S1967-Thermoplastic-Elastomer-TPE.php

Physical Properties	Metric	English	Comments
Density	0.980 g/cc	0.0354 lb/in ³	ISO 1183

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	60	60	ISO 868
Tensile Strength at Break	7.20 MPa	1040 psi	ISO 37
Tensile Stress	1.90 MPa	276 psi	ISO 37
	@Strain 100 %	@Strain 100 %	
Elongation at Break	2.90 MPa	421 psi	ISO 37
	@Strain 300 %	@Strain 300 %	
Tear Strength	28.0 kN/m	160 pli	ISO 34-1
Compression Set	14 %	14 %	ISO 815
	@Temperature 23.0 °C, Time 259000 sec	@Temperature 73.4 °F, Time 72.0 hour	
	60 %	60 %	
	@Temperature 70.0 °C, Time 79200 sec	@Temperature 158 °F, Time 22.0 hour	ISO 815
	93 %	93 %	ISO 815
	@Temperature 100 °C, Time 79200 sec	@Temperature 212 °F, Time 22.0 hour	

Processing Properties	Metric	English	Comments
Melt Temperature	180 - 220 °C	356 - 428 °F	

Processing Properties	Metric 50.0 °C	English 40 °F	Comments
-----------------------	----------------	---------------	----------

Descriptive Properties	Value	Comments
Features	High Flow	
Forms	Pellets	
Generic Material	TPE	
Generic Material Type	Styrenic Thermoplastic Elastomer (TES)	
Generic Name	Thermoplastic Elastomer (TPE)	
Injection Rate	Fast	
Manufacturer / Supplier	GLS Thermoplastic Elastomers	
Processing Method	Injection Molding	
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	
	North America	
	South America	
RoHS Compliance	RoHS Compliant	
Uses	Appliances	
	Automotive Applications	
	Consumer Applications	
	General Purpose	
	Industrial Applications	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China