

## Radici Heraflex® P46D 11 I RB T 200 Modified Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Molded

### Material Notes:

Shore hardness: 46D (3s)Shiny surface, very flexible even at very low T°C (to -30°C), good resistance to weather conditions, very light and recyclableApplication examples: transparent, winter footwear, ski boots, sports shoesInformation provided by Radici group.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Radici-Heraflex-P46D-11-I-RB-T-200-Modified-Polypropylene.php](http://www.lookpolymers.com/polymer_Radici-Heraflex-P46D-11-I-RB-T-200-Modified-Polypropylene.php)

Physical Properties	Metric	English	Comments
Specific Gravity	0.890 g/cc	0.890 g/cc	

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	46	46	
	@Time 3.00 sec	@Time 0.000833 hour	

Thermal Properties	Metric	English	Comments
Minimum Service Temperature, Air	-30.0 °C	-22.0 °F	

Optical Properties	Metric	English	Comments
Transmission, Visible	90 %	90 %	transparent; thickness not quantified

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China