

## SABIC Innovative Plastics NORYL PX1265 PPE+PS (Asia Pacific)

Category : Polymer , Thermoplastic , Polyphenylene Ether/PPO , Polystyrene (PS)

### Material Notes:

Automotive applications. Exterior mirror and cluster housings, speaker grilles, cowl tops, exterior trim. 270F (132C) DTUL.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SABIC-Innovative-Plastics-NORYL-PX1265-PPEPS-Asia-Pacific.php](http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-NORYL-PX1265-PPEPS-Asia-Pacific.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.06 g/cc	1.06 g/cc	ASTM D792
Water Absorption	0.10 %	0.10 %	ASTM D570
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	SABIC Method
	@Thickness 3.20 mm	@Thickness 0.126 in	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	62.0 MPa	8990 psi	Type I, 50 mm/min; ASTM D638
Elongation at Break	35 %	35 %	Type I, 50 mm/min; ASTM D638
Flexural Yield Strength	93.0 MPa	13500 psi	2.6 mm/min, 100 mm span; ASTM D790
Flexural Modulus	2.30 GPa	334 ksi	2.6 mm/min, 100 mm span; ASTM D790
Izod Impact, Notched	2.45 J/cm	4.59 ft-lb/in	ASTM D256
	1.33 J/cm	2.49 ft-lb/in	
	@Temperature -40.0 Â°C	@Temperature -40.0 Â°F	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	72.0 Âµm/m-Â°C	40.0 Âµin/in-Â°F	ASTM E 831
	@Temperature 0.000 - 100 Â°C	@Temperature 32.0 - 212 Â°F	
Deflection Temperature at 0.46 MPa (66 psi)	140 Â°C	284 Â°F	unannealed; ASTM D648
	@Thickness 6.40 mm	@Thickness 0.252 in	
Deflection Temperature at 1.8 MPa (264 psi)	135 Â°C	275 Â°F	unannealed; ASTM D648
	@Thickness 6.40 mm	@Thickness 0.252 in	
UL RTI, Electrical	50.0 Â°C	122 Â°F	UL 746B

Thermal Properties	Metric	English	Comments
UL RTI, Mechanical without Impact	50.0 Â°C	122 Â°F	UL 746B
Flammability, UL94	HB @Thickness 1.47 mm	HB @Thickness 0.0579 in	UL 94

Electrical Properties	Metric	English	Comments
Arc Resistance	60 - 120 sec	60 - 120 sec	Tungsten; ASTM D495
Comparative Tracking Index	175 - 250 V	175 - 250 V	UL 746A
Hot Wire Ignition, HWI	>= 120 sec	>= 120 sec	UL 746A
High Amp Arc Ignition, HAI	15 - 30 arcs	15 - 30 arcs	UL 746A
High Voltage Arc-Tracking Rate, HVTR	>= 150 mm/min	>= 5.91 in/min	UL 746A

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China