

Styrolution Luran® SAN C Styrene Acrylonitrile

Category : Polymer , Thermoplastic , SAN Polymer , Styrene Acrylonitrile (SAN), Transparent

Material Notes:

Luran SAN C is an injection molding grade of SAN with medium impact strength and high flow. Information provided by Styrolution

Order this product through the following link:

http://www.lookpolymers.com/polymer_Styrolution-Luran-SAN-C-Styrene-Acrylonitrile.php

Physical Properties	Metric	English	Comments
Melt Flow	23 g/10 min @Load 10.0 kg, Temperature 220 °C	23 g/10 min @Load 22.0 lb, Temperature 428 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	68.0 MPa	9860 psi	ISO 527

Thermal Properties	Metric	English	Comments
Vicat Softening Point	104 °C @Load 5.10 kg	219 °F @Load 11.2 lb	120°C/h; ASTM D 1525

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China