

Techmer ES Elastoblend® PA6 GF25 IM L 25% Glass Filled

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, 30% Glass Fiber Filled , Nylon 6, Impact Grade

Material Notes:

Availability: North America Forms: Pellets Filler/Reinforcement: Glass Fiber Reinforcement, 25% Filler by Weight Additive: Impact Modifier

Features: Impact Modified Processing Method: Injection Molding Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-Elastoblend-PA6-GF25-IM-L-25-Glass-Filled.php

Physical Properties	Metric	English	Comments
Density	1.27 g/cc	0.0459 lb/in ³	ASTM D792
Water Absorption	0.90 % @Time 86400 sec	0.90 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0010 cm/cm @Thickness 3.17 mm	0.0010 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	112	112	ASTM D785
Tensile Strength, Yield	124 MPa	18000 psi	ASTM D638
Elongation at Break	4.5 %	4.5 %	ASTM D638
Flexural Strength	172 MPa	25000 psi	ASTM D790
Flexural Modulus	6.55 GPa	950 ksi	ASTM D790
Izod Impact, Notched	2.14 J/cm @Thickness 3.17 mm	4.00 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	12.6 Åm/m-Å°C	7.00 Åin/in-Å°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	213 Å°C	415 Å°F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	204 Å°C	400 Å°F	Unannealed; ASTM D648

Electrical Properties	Metric	English	Comments
Volume Resistivity	5.00e+15 ohm-cm	5.00e+15 ohm-cm	ASTM D257
Dielectric Strength	15.7 kV/mm	400 kV/in	Method A (Short-Time); ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China